

*“Compounding for the Best”***AcryliMax 301HP**

Application: Heat resistant flame retardant ABS battery molding compound.

PRODUCT SPECIFICATIONS

Property	Units	Value	Test Method
Density	g/cm ³	1.19 (±0.02)	ASTM D792-91
Melt Flow Rate	g/10 min	8 (±2)	ASTM D1238-95
Tensile Strength @Yield	psi	6100 min	ASTM D638-97
Ultimate Elongation	%	10 min	ASTM D638-97
Flexural Modulus	psi	370,000 min	ASTM D790-97
Flammability	1/8"	V-0	UL-94 V-0
Impact, Gardner (GC)	ft-lb/in	2 min	ASTM D5420-96
Impact, Izod, Notched	ft-lb/in	1.5 min	ASTM D256-97
Heat Deflection Temp	°C	98 min	ASTM D648-97

**Our Staff is available to answer questions and provide technical assistance at
(978) 537-8261**

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261
Sales Fax 978.534.8362 | General Fax 978.537.5310 | www.sespoly.com

08/25/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.