

*“Compounding for the Best”*

**GA-2190E-FR CLEAR**

Application: Specialty clear, 60°C insulating compound designed for excellent clarity and sunlight resistance.

PRODUCT SPECIFICATIONS

Property	Units	Value	Test Method
Durometer	Shore A	95/90(±3)	ASTM D2240
Specific Gravity	g/cm <sup>3</sup>	1.23(±0.03)	ASTM D792
Tensile Strength	psi	2350	ASTM D412
100% Modulus	psi	1350	ASTM D412
Elongation	%	310	ASTM D412
Brittle Point	°C	-30	ASTM D746
Oxygen Index	%	27	ASTM D2863
Weight Loss (7 days @ 100°C)	%	2.2	

**Our Staff is available to answer questions and provide technical assistance at  
(978) 537-8261**

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261  
Sales Fax 978.534.8362 | General Fax 978.537.5310 | [www.sespoly.com](http://www.sespoly.com)

08/28/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.