

*“Compounding for the Best”*

**GF-91-102-2**

Application: Non-migratory, non-contaminating, jacketing material designed to meet the requirements of Mil-C-17G Type 2a. This material has an operating temperature of 85°C to -45°C as per Mil C-17G type 2a specification.

PRODUCT SPECIFICATIONS

Property	Units	Value	Test Method
Specific Gravity	g/cm <sup>3</sup>	1.23(±0.03)	ASTM D792
Durometer	Shore A	73/65(±3)	ASTM D2240
Tensile Strength	psi	1650	ASTM D412
Elongation	%	410	ASTM D412
Oxygen Index	%	26	ASTM D2863
Brittle Point	°C	-45	ASTM D746
Air Oven aged 7 days @ 113°C	°C		
Tensile Strength Retained %	%	105	UL Standard
Elongation Retained %	%	85	UL Standard

**Our Staff is available to answer questions and provide technical assistance at  
(978) 537-8261**

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261  
Sales Fax 978.534.8362 | General Fax 978.537.5310 | [www.sespoly.com](http://www.sespoly.com)

08/29/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.