



“Compounding for the Best”

GPE2001E-ROHS

Application: GPE2001E-ROHS flame retardant polyethylene compound designed for wire and cable applications. GPE2001E-ROHS complies with RoHS requirements. GPE2001E-ROHS is suitable for 75°C continuous use and 100°C Max intermittent temperature application.

PRODUCT SPECIFICATIONS

Property	Units	Typical Value	Test Method
Density	g/cm ³	1.44 (±0.03)	ASTM D792
Melt Flow Index	g/10 min.	2.5 – 5.0	ASTM D1238
Tensile Strength, @ break	PSI	1,100 min.	ASTM D412
Elongation	%	225 min.	ASTM D412
Oxygen Index	%	28 min.	ASTM D2863
Flexural Modulus	PSI	27,500	ASTM D790
Melting Point	°C	85 - 125	DSC
Vicat		TBD	ASTM D1525

Our Staff is available to answer questions and provide technical assistance at (978) 537-8261

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261
Sales Fax 978.534.8362 | General Fax 978.537.5310 | www.sespoly.com

8/6/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.