



“Compounding for the Best”

GTPO8290-GT7

Application: 80°C, Low Smoke, Zero Halogen, Flame Retardant Polyethylene Compound for extrusion applications. Specifically designed to withstand severe UV exposure while maintaining very good color stability. Exhibits excellent processing characteristics at low temperature profile and lower motor load.

PRODUCT SPECIFICATIONS

| Property | Units | Value | Test Method |
|------------------------|-------------------|--------------|-------------|
| Density | g/cm ³ | 1.30 (±0.02) | ASTM D792 |
| Tensile Yield Strength | PSI | 1,200 min | ASTM D638 |
| Elongation @ Break | % | 350 min | ASTM D638 |
| Oxygen Index | % | 27.5 min | ASTM D2863 |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |

Our Staff is available to answer questions and provide technical assistance at (978) 537-8261

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261
Sales Fax 978.534.8362 | General Fax 978.537.5310 | www.sespoly.com

6/19/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.