

*“Compounding for the Best”*

**GTP09008-1**

Application: Non-halogen flame retardant TPO for wire and cable extrusion.

PRODUCT SPECIFICATIONS

Property	Units	Value	Test Method
Specific Gravity	g/cm <sup>3</sup>	1.48	ASTM D792
Tensile Strength	psi	1400	ASTM D638
Elongation	%	300	ASTM D638
Oxygen Index	%	36	ASTM D2863

**Our Staff is available to answer questions and provide technical assistance at  
(978) 537-8261**

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261  
Sales Fax 978.534.8362 | General Fax 978.537.5310 | [www.sespoly.com](http://www.sespoly.com)

08/26/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.