



“Compounding for the Best”

SE900-6

Application: PVC weatherable, integral colored, filled, Roof Ditch Molding Skin which meets the Ford WSK-M4D689-A5

PRODUCT SPECIFICATIONS

Property	Units	Value	Test Method
Durometer, 15 sec	Shore A	75±5	ASTM D2240
Specific Gravity	g/cm ³	1.35 max	ASTM D792,A
Tensile Strength	Mpa	11 min	ASTM D638, Type IV 500mm/min.
Elongation	%	240 min	ASTM D638, Type IV 500mm/min.
Tear	kN/m	40 min	ISO 34, Method B
Cold Flex	°C	-30	FLTM BN 102-01
Accelerated Weathering after 2000 kj/m ²	DE	3.0 max	SAEJ2527

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.