



“Compounding for the Best”

XP11-289A15

Application: PVC weatherable, integral colored, filled, high flow injection molding compound.

PRODUCT SPECIFICATIONS

Property	Units	Value	Test Method
Durometer, 15 sec	Shore D	43 (±5)	ASTM D2240
Specific Gravity	g/cm ³	1.40 max	ASTM D792
Tensile Strength	MPa	17.5 min	ASTM D638
Elongation	%	200 min	ASTM D638
Cold Flexibility	°C	-30	MS-DC-543
Accelerated Weathering after 2500 kJ/m ²	DE	3.0 max	SAEJ2527

Our Staff is available to answer questions and provide technical assistance at (978) 537-8261

140 Leominster-Shirley Road | Lunenburg, MA 01462 | 978.537.8261
Sales Fax: 978.534.8362 | General Fax: 978.537.5310 | www.sespoly.com

6/19/2009

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.