



“Compounding for the Best”

XP44-10MG

Application: PVC weatherable, integral colored, filled, body side end cap molding compound.

PRODUCT SPECIFICATIONS

| Property | Units | Value | Test Method |
|--------------------------------------------------------|-------------------|----------|------------------------------|
| Durometer, 15 sec | Shore D | 37±3 | ISO 868 |
| Specific Gravity | g/cm ³ | 1.40 max | ISO 1183, A |
| Tensile Strength | Mpa | 9 min | ISO 37, Type I 500mm/min. |
| Elongation | % | 75 min | ISO 37, Type I 500mm/min. |
| Cold Flex | °C | -30 | GM9503P |
| Accelerated Weathering after 2000 kj/m ² | DE | 3.0 max | SAEJ2527 |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |

The information presented here is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.